# Carbon and Alloy Steels EN10143 and EN10152



Some Aalco Service Centres now stock a range of Galvanised and Zintec Sheet with coils and blanks also available upon request.

For more information, prices and to place an order please contact the Sales team at your local service centre.

#### **ALLOY DESIGNATIONS**

The Galvanised Sheet is Grade DX51DZ + 275 MAC TO EN10143: 2006 The Zintec Sheet is Grade DC01 ZE25 DSAP&T TO EN10152

### **GALVANISED SHEET**

Grade DX51DZ + 275 MAC TO EN10143: 2006

Length (mm)	Width (mm)	Thickness (mm)	Weight: Kg per Sheet
2000	1000	0.7	10.99
2500	1250	0.7	17.2
2000	1000	0.8	12.6
2500	1250	0.8	19.6
2000	1000	0.9	14.1
2500	1250	0.9	22.1
2000	1000	1.2	18.8
2500	1250	1.2	29.5
2000	1000	1.5	23.6
2500	1250	1.5	36.8
2000	1000	2.0	31.4
2500	1250	2.0	49.1
3000	1500	2.0	70.7
2000	1000	3.0	47.1
2500	1250	3.0	73.6
3000	1500	3.0	106.0

### ZINTEC SHEET

Grade DC01 ZE25 DSAP&T TO EN10152

_				
	Length (mm)	Width (mm)	Thickness 9mm)	Weight: Kg per Sheet
	2000	1000	0.7	10.99
	2500	1250	0.7	17.2
	2000	1000	0.9	14.1
	2500	1250	0.9	22.1
	2500	1250	1.2	29.5
	2500	1250	1.5	36.8
	2500	1250	2.0	49.1
	2500	1250	3.0	73.6

## Carbon and Alloy Steels EN10143 and EN10152



### CONTACT

Address: Please make contact directly with your local service centre, which can be found via the Locations page of our web site

Web: www.aalco.co.uk

### **REVISION HISTORY**

Datasheet Updated 18 July 2019

### **DISCLAIMER**

This Data is indicative only and as such is not to be relied upon in place of the full specification. In particular, mechanical property requirements vary widely with temper, product and product dimensions. All information is based on our present knowledge and is given in good faith. No liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon.

Please note that the 'Datasheet Update' date shown above is no guarantee of accuracy or whether the datasheet is up to date.

The information provided in this datasheet has been drawn from various recognised sources, including EN Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources.

Material supplied by the Company may vary significantly from this data, but will conform to all relevant and applicable standards.

As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied.

Advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company. All transactions are subject to the Company's current Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.

[2 OF 2]